



CAPILEX 20

Solvent Resistant Capillary Film

DESCRIPTION

Capillex films are precision coated, pre-sensitised capillary photostencil films, which are adhered to the mesh with water prior to exposure.

The films are coated onto a 75µ [3 thou) polyester base. The films have been designed for use with solvent based or UV curing inks.

Applications

The high print quality and excellent durability of Capillex 20 makes it perfect for fine line printing.

Electronics
Industrial marking
Graphics

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

FEATURES & BENEFITS

- Capillex 20 has been specifically developed for printing fine line images where quality, consistency and durability are essential.
- Mesh range 100 to 140/cm [250 to 355/inch).
- Easy to use.
- Wide processing latitude.
- Very good print quality -perfect for fine line printing.
- Very tough, suitable for use with solvent and UV inks.
- Simple to decoat.

WORKING INSTRUCTIONS

Mesh Preparation

All new synthetic monofilament meshes should be abraded with Autoprep Gel before use. [Used meshes should be re-abraded after every 5 stencils).

All meshes should be degreased using Universal Mesh Prep immediately prior to mounting the film.

ADHERING TO THE MESH

For large or small screens:

For best results use the Caplicator film applicator. Cut the film to size and place the film on a dry, flat surface. Using the Autotype Anti-Static Duster, remove dust from the polyester as the film is rolled, emulsion side out, leaving approximately 2 cm [$\frac{3}{4}$ inch) unrolled. Place the film inside the Caplicator. Spray the mesh with water and wipe excess water from the perimeter of the frame to avoid rivulets after adhering the film.

Contact the rolled film leading edge onto the top of the wet vertical screen and unroll the film down the screen, thus adhering it to the mesh. Remove excess moisture from the inside of the screen with a lightweight, window cleaner type squeegee. Wipe excess water from the perimeter of the frame with absorbent cloth then proceed to drying.

For small screens only:-

Place the film emulsion side up onto a raised pad and lay the dry degreased screen on top. Using a hand spray water bottle, spray water onto the mesh until the film is completely wet. Then squeegee off excess water from the inside of the screen. Wipe water from the perimeter of the frame then proceed to drying.

For more information on how to apply Capillex film, go to the How to Guide section at macdermid.com/Autotype.

PACKAGING

The screen can be dried with cold or warm air, maximum 30 °C [86 °F). Thorough drying is essential for optimum results. When the support has been peeled off continue drying for a few minutes to ensure the film is completely dry.

EXPOSURE

Correct exposure is essential for optimum stencil performance. Underexposure will give a weak stencil and reduce resistance.

Remove dust from the surface of the stencil and tape positive in position. Place entire screen in a suitable vacuum frame and expose. We recommend use of the Autotype Exposure Calculator for test exposures to ascertain correct timing.

WASHOUT & DRYING

Wash out the screen from both sides with a strong spray of water. Continue the washout until all parts of the image appear clean and sharp. Blot off surplus moisture and dry at a maximum temperature of 30 °C [86 °F].

Spot out pinholes with sensitised emulsion.

BLOCKOUT

Block out the area between the edge of the stencil and the frame with Regular, Thick or Blue Filler when using solvent based or UV curing inks.

SHELF LIFE & STORAGE

Remove ink from the screen with an Autosolve screen cleaner. Then apply Autostrip to both sides of the screen and leave to stand for 5 minutes. The stencil can then be removed with a strong water jet. If a stain or ghost image still remains, use Autokleen Plus.

For more information on how to use MacDermid Autotype products, go to the How to Guide section at macdermid.com/autotype.

SHELF LIFE & STORAGE

The film should be kept in the protective packaging supplied. Store in a cool place away from hot drying cupboards and radiators. Do not store in a damp place. Correct storage conditions are at a temperature of 5 to 20 °C [40 to 86 °F] and at a relative humidity of 45-60%.

Shelf life at these conditions is 18 months.

PACKAGING

Capillex is available in roll widths of 61 cm, 104 cm and 122 cm wide [24 in, 41 in and 48 in) and in a variety of lengths. Custom cut sheets are available upon request.

SAFETY & WARNING

MacDermid Autotype recommends that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use.

Safety Data Sheets are available from MacDermid Autotype.

WASTE TREATMENT

Prior to using any recommendations or suggestions by MacDermid Autotype for waste treatment, the user is required to know the appropriate local/state/federal regulations for onsite or off-site treatment which may require permits. If there is any conflict regarding our recommendations, local/state/federal regulations take precedent.